AD

TECHNICAL REPORT ARLCB-TR-81038

ELASTIC-PLASTIC THICK-WALLED TUBES SUBJECTED TO INTERNAL PRESSURE AND TEMPERATURE GRADIENT

P. C. T. Chen

September 1981

US ARMY ARMAMENT RESEARCH AND DEVELOPMENT COMMAND
LARGE CALIBER WEAPON SYSTEMS LABORATORY
BENÉT WEAPONS LABORATORY
WATERVLIET, N. Y. 12189

DTIC
ELECTE
OCT 6 1981

A

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

81 10 5 003

DISCLAIMER

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

The use of trade name(s) and/or manufacture(s) does not constitute an official indorsement or approval.

DISPOSITION

Destroy this report when it is no longer needed. Do not return it to the originator.

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER ARLCB-TR-81038	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) ELASTIC-PLASTIC THICK-WALLED TUBES SUBJECTED TO INTERNAL PRESSURE AND TEMPERATURE GRADIENT		5. TYPE OF REPORT & PERIOD COVERED Final
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) P. C. T. Chen		8. CONTRACT OR GRANT NUMBER(s)
9. PERFORMING ORGANIZATION NAME AND ADDRESS US Army Armament Research & Development Command Benet Weapons Laboratory, DRDAR-LCB-TL Watervliet, NY 12189		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS AMCMS No. 611102H5710011 DA Project No. 1L161102BH57 PRON No. 1A1235821A1A
11. CONTROLLING OFFICE NAME AND ADDRESS US Army Armament Research & Development Command Large Caliber Weapon Systems Laboratory Dover, NJ 07801		12. REPORT DATE September 1981
		13. NUMBER OF PAGES 18
14. MONITORING AGENCY NAME & ADDRESS(if different from Controlling Office)		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE

16. DISTRIBUTION STATEMENT (of this Report)

Approved for public release; distribution unlimited.

17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)

19. KEY WORDS (Continue on reverse side if necessary and identify by block number)
Elastic-Plastic
Thick-Walled Tube
Finite-Difference Method
Internal Pressure
Temperature Gradient

20. ABSTRACT (Continue on reverse side if necessary and identify by block number)

Using von Mises' criterion and the Prandtl-Reuss flow theory, numerical solutions are obtained for the stresses, strains, and displacements in an elastic-plastic thick-walled tube subjected to internal pressure and temperature gradient. The material is based on the incremental finite-difference method in conjunction with a scaled loading approach. All incremental quantities are determined in the program and no iteration is needed. The approach is simpler than others yet quite general and accurate.

DD FORM 1473 EDITION OF 1 NOV 65 IS OBSOLETE

TABLE OF CONTENTS

LIST OF ILLUSTRATIONS

1

INTRODUCTION

The elastic-plastic problems of thick-walled tubes subjected to mechanical loadings have been solved by many investigators based on different theories or methods.[1-4] Very little work has been done on the elastoplastic solutions for thick-walled tubes subjected to thermal loadings.[5-7] Recently, a new finite-difference approach was developed for solving the plane-strain problems of elastic-plastic thick-walled tubes subjected to mechanical loadings[3] or thermal loadings.[7] The approach has been extended to solve the generalized plane-strain problem subjected to mechanical loadings.[4]

In the present report, the generalized plane-strain problems of elastic-plastic thick-walled tubes subjected to mechanical as well as thermal loadings are considered. The formulation includes internal pressure, external pressure, axial force, steady or transient thermal loadings. The numerical result is reported for a closed-end tube subjected to internal pressure and to temperature gradient. The formulation is based on the incremental finite-difference method using von Mises' criterion, the Prandtl-Reuss flow theory and the isotropic hardening rule. All incremental quantities are determined in the program and no iteration is needed. In order to improve the efficiency of the program, a scaled loading approach has been implemented. The numerical results have been compared with those of Bland[5] and additional results due to large temperature gradient are reported.

References are listed at the end of this report.

BASIC EQUATIONS

Assuming small strain and no body forces in the axisymmetric state of generalized plane strain, the radial and tangential stresses, σ_r and σ_θ, must satisfy the equilibrium equation,

$$r(\partial\sigma_r/\partial r) = \sigma_\theta - \sigma_r \; ; \qquad (1)$$

and the corresponding strains, ε_r and ε_θ, are given in terms of the radial displacement, u, by

$$\varepsilon_r = \partial u/\partial r \quad , \quad \varepsilon_\theta = u/r \quad . \qquad (2)$$

It follows that the strains must satisfy the equation of compatibility

$$r(\partial\varepsilon_\theta/\partial r) = \varepsilon_r - \varepsilon_\theta \quad . \qquad (3)$$

Whereas the differential equations (1), (2), and (3) hold throughout the tube regardless of the material properties, the constitution equations assume various forms according to the adopted form of yield function, hardening rule, total or incremental theory of plasticity. In the present report, the material is assumed to be elastic-plastic, obeying the von Mises' yield criterion, the Prandtl-Reuss flow theory and the isotropic hardening law. The complete stress-strain relations are:

$$\Delta\varepsilon_i' = \Delta\sigma_i'/2G + (3/2)\sigma_i'\Delta\sigma/(\sigma H') \qquad (4)$$

$$\Delta\sigma > 0 \quad \text{for} \quad i = r,\theta,z$$

$$\Delta\varepsilon_m = E^{-1}(1-2\nu)\Delta\sigma_m + \alpha\Delta T \qquad (5)$$

where E, ν, α are Young's modulus, Poisson's ratio, coefficient of thermal expansion, respectively, ΔT is the temperature increment,

2

$$2G = E/(1+\nu) \quad ,$$

$$\varepsilon_m = (\varepsilon_r + \varepsilon_\theta + \varepsilon_z)/3 \quad , \quad \varepsilon_1' = \varepsilon_1 - \varepsilon_m \quad ,$$

$$\sigma_m = (\sigma_r + \sigma_\theta + \sigma_z)/3 \quad , \quad \sigma_1' = \sigma_1 - \sigma_m \quad ,$$

$$\sigma = (1/\sqrt{2})[(\sigma_r - \sigma_\theta)^2 + (\sigma_\theta - \sigma_z)^2 + (\sigma_z - \sigma_r)^2]^{1/2} > \sigma_0 \quad , \tag{6}$$

and σ_0 is the yield stress in simple tension or compression. For a strain-hardening material, H' is the slope of the effective stress/plastic strain curve

$$\sigma = H(\int d\varepsilon^p) \quad . \tag{7}$$

For an ideally-plastic material ($H' = 0$), the quantity $(3/2)d\sigma(\sigma H')$ is replaced by $d\lambda$, a positive factor of proportionality. When $\sigma < \sigma_0$ or $d\sigma < 0$, the state of stress is elastic and the second term in equation (4) disappears. Following Yamada et al,[8] equations (4) and (5) can be rewritten in an incremental form

$$\Delta\sigma_i = d_{ij}\Delta\varepsilon_j - E\alpha\Delta T/(1-2\nu) \quad \text{for} \quad i,j = r,\theta,z$$

and

$$d_{ij}/2G = \nu/(1-2\nu) + \delta_{ij} - \sigma_i'\sigma_j'/S \quad , \tag{8}$$

where

$$S = \frac{2}{3}(1 + \frac{1}{3}H'/G)\sigma^2 \quad , \quad H'/E = \omega/(1-\omega) \quad , \tag{9}$$

ωE is the slope of the effective stress-strain curve, and δ_{ij} is the Kronecker delta.

Consider an open-end or closed-end thick-walled tube of inner radius a and external radius b. The tube is subjected to inner pressure p, external pressure q, and force f, inner temperature T_a and external temperature T_b. The boundary conditions for the problem are

3

$$\sigma_r(a,t) = -p \quad , \quad \sigma_r(b,t) = -q \quad ,$$

$$2\pi \int_a^b r\sigma_z dr = \mu\pi a^2 p + f \tag{10}$$

where μ is 0 for open-end tubes and 1 for closed-end tubes.

When the temperature T is not varying with respect to time, the steady state distribution is given by

$$T = T_a + N \log (r/a)$$

and

$$N = (T_b - T_a)/\log (b/a) \tag{11}$$

The stress solution in the elastic range is well-known. The quantities p^*, q^*, f^*, T_a^* or T_b^* required to cause initial yielding can be determined by using the von Mises' yield criterion.

FINITE-DIFFERENCE FORMULATION

For loading beyond the elastic limit, an incremental approach of the finite-difference formulation is used. The cross section of the tube is divided into n rings with $r_1=a, r_2, \ldots, r_k=\rho, \ldots, r_{n+1}=b$, where ρ is the radius of the elastic-plastic interface. At the beginning of each increment of loading, the distribution of temperature, displacements, strains, and stresses is assumed to be known and we want to determine Δu, $\Delta\varepsilon_r$, $\Delta\varepsilon_\theta$, $\Delta\varepsilon_z$, $\Delta\sigma_r$, $\Delta\sigma_\theta$, $\Delta\sigma_z$ at all grid points for the applied incremental loading, Δp, Δq, Δf, ΔT_i (i = 1 to n+1). Since the incremental stresses are related to the incremental strains by the incremental form (Eq. (8)) and $\Delta u = r\Delta\varepsilon_\theta$, there exists only three unknowns at each station that have to be determined for each increment of loading. Accounting for the fact that the axial strain ε_z is independent of r, the unknown variables in the present formulation are $(\Delta\varepsilon_\theta)_i$, $(\Delta\varepsilon_r)_i$, for

4

$i = 1, 2, \ldots, n, n+1$, and $\Delta\epsilon_z$.

The equation of equilibrium (1) and the equation of compatibility (3) are valid for both the elastic and the plastic regions of a thick-walled tube. The finite-difference forms of these two equations at $i = 1, \ldots, n$ are given by

$$(r_{i+1} - 2r_i)(\Delta\sigma_r)_i - (r_{i+1} - r_i)(\Delta\sigma_\theta)_i + r_i(\Delta\sigma_r)_{i+1}$$
$$= (r_{i+1} - r_i)(\sigma_\theta - \sigma_r)_i - r_i[(\sigma_r)_{i+1} - (\sigma_r)_i] \qquad (12)$$

for the equation of equilibrium, and

$$(r_{i+1} - 2r_i)(\Delta\epsilon_\theta)_i - (r_{i+1} - r_i)(\Delta\epsilon_r)_i + r_i(\Delta\epsilon_\theta)_{i+1}$$
$$= (r_{i+1} - r_i)(\epsilon_r - \epsilon_\theta)_i - r_i[(\epsilon_\theta)_{i+1} - (\epsilon_\theta)_i] \qquad (13)$$

for the equation of compatibility. With the aid of the incremental stress-strain relations (Eq. (8)), equation (12) can be rewritten as

$$[(r_{i+1} - 2r_i)(d_{12})_i + (-r_{i+1} + r_i)(d_{22})_i](\Delta\epsilon_\theta)_i$$
$$+ [(r_{i+1} - 2r_i)(d_{11})_i + (-r_{i+1} + r_i)(d_{21})_i](\Delta\epsilon_r)_i$$
$$+ r_i(d_{12})_{i+1}(\Delta\epsilon_\theta)_{i+1} + r_i(d_{11})_{i+1}(\Delta\epsilon_r)_{i+1}$$
$$+ [(r_{i+1} - 2r_i)(d_{13})_i + (-r_{i+1} + r_i)(d_{23})_i + r_i(d_{13})_{i+1}]\Delta\epsilon_z$$
$$= (r_{i+1} - r_i)(\sigma_\theta - \sigma_r)_i - r_i[(\sigma_r)_{i+1} - (\sigma_r)_i]$$
$$+ r_i E\alpha(1-2\nu)^{-1}(\Delta T_{i+1} - \Delta T_i) \quad . \qquad (14)$$

The boundary conditions for the problem are

$$\Delta\sigma_r(a,t) = -\Delta p \quad , \quad \Delta\sigma_r(b,t) = -\Delta q \quad ,$$
$$\pi \sum_{i=1}^{n} [r_i(\Delta\sigma_z)_i + r_{i+1}(\Delta\sigma_z)_{i+1}](r_{i+1} - r_i) = \mu\pi a^2 \Delta p + \Delta f \quad , \qquad (15)$$

where μ is 0 for open-end tubes and 1 for closed-end tubes. Using the incremental relations (Eq. (8)), we rewrite equation (15) as

$$(d_{12})_1(\Delta\varepsilon_\theta)_1 + (d_{11})_1(\Delta\varepsilon_r)_1 + (d_{13})_1\Delta\varepsilon_z = -\Delta\rho + E\alpha(1-2\nu)^{-1}\Delta T_1 \quad (16)$$

$$(d_{12})_{n+1}(\Delta\varepsilon_\theta)_{n+1} + (d_{11})_{n+1}(\Delta\varepsilon_r)_{n+1} + (d_{13})_{n+1}\Delta\varepsilon_z = -\Delta q + E\alpha(1-\nu)^{-1}\Delta T_{n+1}$$

$$(17)$$

and

$$\sum_{i=1}^{n} (r_{i+1}-r_i)\{r_i[(d_{23})_i(\Delta\varepsilon_\theta)_i + (d_{13})_i(\Delta\varepsilon_r)_i] + r_{i+1}[(d_{23})_{i+1}(\Delta\varepsilon_\theta)_{i+1}$$

$$+ (d_{13})_{i+1}(\Delta\varepsilon_r)_{i+1}]\} + \sum_{i=1}^{n} (r_{i+1}-r_i)[r_i(d_{33})_i + r_{i+1}(d_{33})_{i+1}]\Delta\varepsilon_z$$

$$= \mu a2\Delta p + \Delta f/\pi + \sum_{i=1}^{n} (r_{i+1}-r_i)[r_i\Delta T_i + r_{i+1}\Delta T_{i+1}]E\alpha/(1-2\nu) \quad (18)$$

Now we can form a system of $2n+3$ equations for solving $2n+3$ unknowns, $(\Delta\varepsilon_\theta)_i$, $(\Delta\varepsilon_r)_i$, at $i = 1,2,\ldots,n,n+1$ and $\Delta\varepsilon_z$. Equations (16), (17), and (18) are taken as the first and last two equations, respectively, and the other $2n$ equations are set up at $i = 1,2,\ldots,n$ using equations (13) and (14). The *final system is an unsymmetric matrix of arrow type with the nonzero terms appearing in the last row and column and others clustered about the main diagonal, two below and one above.*

INCREMENTAL LOADING - FIXED VS. SCALED

When the total applied pressure p or temperature $T_i(i=1$ to $n+1)$ is given, it is natural to divide the loading path into m equal fixed increments such as $\Delta p = (p-p^*)/m$, $\Delta T_i = (T_i-T_i^*)/m$. These fixed increments need not be equal for all steps and any sequence of m increments can be supplied by the user. A sequence of decreasing load-increments is a better choice than that of equal increments.

6

In order to increase the efficiency of the program, an adaptive algorithm based on a scaled incremental-loading approach[8] has been implemented. In each step, a dummy load-increment such as Δp is applied and the incremental results $\Delta\sigma_i$ for $i = r,\theta,z$ at all grids are determined. For all grid points at which $\sigma = ||\sigma_i|| < \sigma_0$, we compute the scaler α's by the formula

$$\alpha = \frac{1}{2} \{\Gamma + [\Gamma^2 + 4||\Delta\sigma_i||^2(\sigma_0^2 - ||\sigma_i||^2)]^{1/2}\}/||\Delta\sigma_i||^2 \quad , \qquad (19)$$

where

$$\Gamma = ||\sigma_i||^2 + ||\Delta\sigma_i||^2 - ||\sigma_i + \Delta\sigma_i||^2 \quad , \qquad (20)$$

and $||\sigma_i||^2$, $||\Delta\sigma_i||^2$, $||\sigma_i + \Delta\sigma_i||^2$ are computed by

$$||\sigma_i||^2 = \frac{1}{2} [(\sigma_r - \sigma_\theta)^2 + (\sigma_\theta - \sigma_z)^2 + (\sigma_z - \sigma_r)^2] \quad . \qquad (21)$$

Let λ be the minimum of the α's. Then λ is the load-increment factor just sufficient to yield one additional point. A sequence of $\lambda(j)$ can be determined for all steps $j = 1,2,\ldots,m$ and the updated results are

$$p(j) = p(j-1) + \lambda(j)\Delta p(j)$$

$$\sigma_i(j) = \sigma_i(j-1) + \lambda(j)\Delta\sigma_i(j) \quad , \quad \text{etc.} \qquad (22)$$

NUMERICAL RESULTS AND DISCUSSIONS

Consider a closed-end tube subjected to internal pressure p, inner and outer temperature T_a and T_b. The numerical results were based on the following parameters: b = 2", a = 1", n = 100, ν = 0.3, E = 30×10^6 psi, σ_0 = 30×10^3 psi, ω = 0, α = 7.75×10^{-6} in/in°F.

According to Bland,[5] let us define

$$\theta = E\alpha N/[2(1-\nu)\sigma_0/\sqrt{3}]$$

7

as a measure of the effect of the temperature differences in the stress system. The mean temperature

$$T_N = 2(b^2-a^2)^{-1} \int_a^b Tr\,dr$$

is taken as zero in the calculation of u/r. Three values of the temperature stress factor θ are chosen: θ = -1/2, 0, and 1/2, i.e., T_b-T_a = -72.3°F, 0°F, and 72.3°F. The thermal stresses are in the elastic range. In the presence of these temperature gradients, internal pressure p is applied incrementally until the fully plastic state is reached. The internal pressure p and inside displacement U_a are obtained as functions of elastic-plastic interface ρ as shown in Figure 1. The effect of temperature gradient on these relations is clearly shown in the figure. In order to compare the results by Bland,[5] the state of stress is evaluated at ρ/a = 1.73. The dimensionless stresses $(\sigma_r, \sigma_\theta, \sigma_z)/\sigma_0$ are expressed as functions of r/a as shown in Figures 2 through 4 for three cases of θ = 0, -1/2, 1/2, respectively.

After removing the temperature gradients and internal pressure, the residual stresses were obtained for all three cases. The states of residual stresses for the first two cases were still elastic but reverse yielding occurred when unloading the last case. Five scaled incremental-loading steps and one applied incremental-loading step were needed to unload completely. The residual stresses for the last case are shown in Figure 5. The results in Figures 1 through 5 are roughly the same as those of Bland[5] except σ_z. This difference is reasonable because Tresca's yield criterion is used in reference 5.

As a last example let us consider a closed-end tube subjected to inner temperature T_a only. When the temperature gradient is of sufficient magnitude, yielding will first expand from the inside. When T_a is larger than a certain limit (238.4°F), plastic zone will expand from both the inside and outside surface toward the interior. The relation between the inside temperature and elastic-plastic interface is shown in Figure 6. The stresses in a closed-end tube subjected to temperature gradient (T_a = 299°F, T_b = 0) are shown in Figure 7. The dotted lines are elastic-plastic interfaces.

REFERENCES

1. S. C. Chu, "A More Rational Approach to the Problem of an Elastoplastic Thick-Walled Cylinder," J. of the Franklin Institute, Vol. 294, 1972, pp. 57-62.

2. P. C. T. Chen, "The Finite-Element Analysis of Elastic-Plastic Thick-Walled Tubes," Proceedings of Army Symposium on Solid Mechanics, 1972, pp. 243-253.

3. P. C. T. Chen, "A Finite Difference Approach to Axisymmetric Plane-Strain Problems Beyond the Elastic Limit," Transactions of the Twenty-Fifth Conference of Army Mathematicians, pp. 455-465, January 1980.

4. P. C. T. Chen, "Generalized Plane-Strain Problems in an Elastic-Plastic Thick-Walled Cylinder," Transactions of the Twenty-Sixth Conference of Army Mathematicians, pp. 265-275, January 1981.

5. D. R. Bland, "Elastoplastic Thick-Walled Tubes of Work-Hardening Material Subject to Internal and External Pressures and to Temperature Gradients," Journal of the Mechanics and Physics of Solids, 1956, Vol. 4, pp. 209-229.

6. S. C. Chu, "A Numerical Thermo-Elastic-Plastic Solution of a Thick-Walled Tube," AIAA Journal, Vol. 12, No. 3, February 1974, pp. 176-179.

7. J. D. Vasilakis and P. C. T. Chen, "Thermo-Elastic-Plastic Stresses in Hollow Cylinders Due to Quenching," Transactions of the Twenty-Fifth Conference of Army Mathematicians, pp. 661-674, January 1980.

8. Y. Yamada, N. Yoshimura, and T. Sakuri, "Plastic Stress-Strain Matrix and Its Application For the Solution of Elastic-Plastic Problems by the Finite Element," International Journal of Mechanical Sciences, 1968, Vol. 10, pp. 343-354.

Figure 1. Internal pressure and displacement as functions of elastic-plastic interface in a closed-end tube. (a) Internal pressure; (b) Internal displacement.

Figure 2. Stresses in a closed-end tube subjected to internal pressure ($\rho/a = 1.73$; $\theta = 0$).

Figure 3. Stresses in a closed-end tube subjected to internal pressure and temperature gradient (ρ/a = 1.73; θ = -1/2).

Figure 4. Stresses in a closed-end tube subjected to internal pressure and temperature gradient ($\rho/a = 1.73$; $\theta = 1/2$).

14

Figure 5. Residual stresses in a closed-end tube, unloading from Figure 4, $1.04 < \rho/a < 1.05$.

15

Figure 6. The relation between internal temperature and elastic-plastic interface, $T_b = 0$.

16

Figure 7. Stresses in a closed-end tube subjected to temperature gradient, $T_b = 0$.

TECHNICAL REPORT INTERNAL DISTRIBUTION LIST

	NO. OF COPIES
COMMANDER	1
CHIEF, DEVELOPMENT ENGINEERING BRANCH	1
ATTN: DRDAR-LCB-DA	1
-DM	1
-DP	1
-DR	1
-DS	1
-DC	1
CHIEF, ENGINEERING SUPPORT BRANCH	1
ATTN: DRDAR-LCB-SE	1
-SA	1
CHIEF, RESEARCH BRANCH	2
ATTN: DRDAR-LCB-RA	1
-RC	1
-RM	1
-RP	1
CHIEF, LWC MORTAR SYS. OFC.	1
ATTN: DRDAR-LCM	1
CHIEF, IMP. 81MM MORTAR OFC.	1
ATTN: DRDAR-LCB-I	1
TECHNICAL LIBRARY	5
ATTN: DRDAR-LCB-TL	
TECHNICAL PUBLICATIONS & EDITING UNIT	2
ATTN: DRDAR-LCB-TL	
DIRECTOR, OPERATIONS DIRECTORATE	1
DIRECTOR, PROCUREMENT DIRECTORATE	1
DIRECTOR, PRODUCE ASSURANCE DIRECTORATE	1

NOTE: PLEASE NOTIFY ASSOC. DIRECTOR, BENET WEAPONS LABORATORY, ATTN:
DRDAR-LCB-TL, OF ANY REQUIRED CHANGES.

TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST

	NO. OF COPIES		NO. OF COPIES
ASST SEC OF THE ARMY RESEARCH & DEVELOPMENT ATTN: DEP FOR SCI & TECH THE PENTAGON WASHINGTON, D.C. 20315	1	COMMANDER US ARMY TANK-AUTMV R&D COMD ATTN: TECH LIB - DRDTA-UL MAT LAB - DRDTA-RK WARREN MICHIGAN 48090	1 1
COMMANDER US ARMY MAT DEV & READ. COMD ATTN: DRCDE 5001 EISENHOWER AVE ALEXANDRIA, VA 22333	1	COMMANDER US MILITARY ACADEMY ATTN: CHMN, MECH ENGR DEPT WEST POINT, NY 10996	1
COMMANDER US ARMY ARRADCOM ATTN: DRDAR-LC	1	COMMANDER REDSTONE ARSENAL ATTN: DRSMI-RB -RPS -RSM ALABAMA 35809	2 1 1
-LCA (PLASTICS TECH EVAL CEN)	1		
-LCE -LCM -LCS -LCW -TSS(STINFO) DOVER, NJ 07801	1 1 1 1 2	COMMANDER ROCK ISLAND ARSENAL ATTN: SARRI-ENM (MAT SCI DIV) ROCK ISLAND, IL 61202	1
COMMANDER US ARMY ARRCOM ATTN: DRSAR-LEP-L ROCK ISLAND ARSENAL ROCK ISLAND, IL 61299	1	COMMANDER HQ, US ARMY AVN SCH ATTN: OFC OF THE LIBRARIAN FT RUCKER, ALABAMA 36362	1
DIRECTOR US Army Ballistic Research Laboratory ATTN: DRDAR-TSB-S (STINFO) ABERDEEN PROVING GROUND, MD 21005	1	COMMANDER US ARMY FGN SCIENCE & TECH CEN ATTN: DRXST-SD 220 7TH STREET, N.E. CHARLOTTESVILLE, VA 22901	1
COMMANDER US ARMY ELECTRONICS COMD ATTN: TECH LIB FT MONMOUTH, NJ 07703	1	COMMANDER US ARMY MATERIALS & MECHANICS RESEARCH CENTER ATTN: TECH LIB - DRXMR-PL WATERTOWN, MASS 02172	2
COMMANDER US ARMY MOBILITY EQUIP R&D COMD ATTN: TECH LIB FT BELVOIR, VA 22060			

NOTE: PLEASE NOTIFY COMMANDER, ARRADCOM, ATTN: BENET WEAPONS LABORATORY, DRDAR-LCB-TL, WATERVLIET ARSENAL, WATERVLIET, N.Y. 12189, OF ANY REQUIRED CHANGES.

	NO. OF COPIES		NO. OF COPIES
COMMANDER US ARMY RESEARCH OFFICE P.O. BOX 12211 RESEARCH TRIANGLE PARK, NC 27709	1	COMMANDER DEFENSE TECHNICAL INFO CENTER ATTN: DTIA-TCA CAMERON STATION ALEXANDRIA, VA 22314	12
COMMANDER US ARMY HARRY DIAMOND LAB ATTN: TECH LIB 2300 POWDER MILL ROAD ADELPHIA, MD 20783	1	METALS & CERAMICS INFO CEN BATTELLE COLUMBUS LAB 505 KING AVE COLUMBUS, OHIO 43201	1
DIRECTOR US ARMY INDUSTRIAL BASE ENG ACT ATTN: DRXPE-MT ROCK ISLAND, IL 61201	1	MECHANICAL PROPERTIES DATA CTR BATTELLE COLUMBUS LAB 505 KING AVE COLUMBUS, OHIO 43201	1
CHIEF, MATERIALS BRANCH US ARMY R&S GROUP, EUR BOX 65, FPO N.Y. 09510	1	MATERIEL SYSTEMS ANALYSIS ACTV ATTN: DRXSY-MP ABERDEEN PROVING GROUND MARYLAND 21005	1
COMMANDER NAVAL SURFACE WEAPONS CEN ATTN: CHIEF, MAT SCIENCE DIV DAHLGREN, VA 22448	1		
DIRECTOR US NAVAL RESEARCH LAB ATTN: DIR, MECH DIV CODE 26-27 (DOC LIB) WASHINGTON, D. C. 20375	1 1		
NASA SCIENTIFIC & TECH INFO FAC P. O. BOX 8757, ATTN: ACQ BR BALTIMORE/WASHINGTON INTL AIRPORT MARYLAND 21240	1		

NOTE: PLEASE NOTIFY COMMANDER, ARRADCOM, ATTN: BENET WEAPONS LABORATORY, DRDAR-LCB-TL, WATERVLIET ARSENAL, WATERVLIET, N.Y. 12189, OF ANY REQUIRED CHANGES.

ATE

MED

8